

ArmD[®] NIR-Ge

Ge-doped silica/silica fiber

Armadillo ArmD[®] NIR-Ge fibers distinguish themselves with maximum numerical aperture values, unparalleled performance, and an extensive spectral range. Offering a wide range of core diameter options and customizable solutions, these fibers can be tailored to meet your specific needs.

Wavelength	Numerical Aperture (NA)
ArmD [®] NIR-Ge 400 - 2600 nm	Standard 0.37 ± 0.02

Jacketing Options:
 Polyimide: -190 to +350°C
 ETFE (Tefzel[®]): -40 to +150°C
 Nylon: -40 to +100°C
 Acrylate: -40 to +85°C
 DuPont Hytrel[®] 7246: -40 to +140°C
 Acrylate DeSolite[®] DF-0009: -40 to 150°C
 PFA Fluon[®]: -200° to +260°C

Advantages

- Germanium-doped silica glass core
- High resistance against laser damage
- Step-index profile
- Special jackets available for high temperatures, high vacuum and harsh chemicals
- Very low NA expansion
- Biocompatible material
- Sterilizable using ETO and other methods



Technical data

Operating temperature	-200 to +350 °C
Core diameter	Available from 20 to 1000 μm
Standard core / cladding ratios	1 : 1.04 1 : 1.06 1 : 1.1 1 : 1.15 1 : 1.2 1 : 1.25 1 : 1.4 or customized
Standard proof test	100 kpsi (nylon, ETFE, acrylate jacket) 70 kpsi (polyimide jacket)
Minimum bending radius	50 × cladding diameter (short-term mechanical stress) 150 × core diameter (during use with high laser power)



armadillosia.com
 +1-408-900-8883
 info@armadillosia.com

